

CETOL GUPA

TECH SHEET



DESCRIPTION

Fast drying filler / stopper for interior and exterior use. Available in five “wood” colours, it is recommended for use with clear or coloured Transparent Wood Finishes, Varnishes etc.

GENERAL NOTES

Main Characteristics	<ul style="list-style-type: none"> • Nitro-cellulose binder. • Fast drying. • Good adhesion to bare wood, finishes, varnishes etc. • Good response to sanding.
Uses	As filler / stopper for small nail holes and cracks.

APPLICATION DATA

Temperature of Application	5 — 30°C.										
Method	<p>By filling knife. Fill slightly ‘proud’ and allow to dry. Fill larger holes in steps, allowing previous fill to set. (Drying time will vary according to thickness of layers).</p> <p>Rub down with a fine grade silicon carbide paper prior to application of Cetol HLSe, Cetol Filter 7 Plus or Cetol TS Interior Mat Plus.</p> <p>Alternatively, it may be applied after the first coat of stain, but take care to avoid damaging the surrounding surface of woodstain when sanding.</p> <p>After sanding, Cetol Gupa may be treated like wood. In exterior locations, ensure Cetol Gupa is well overcoated with stain or paint.</p>										
Cleaning of Equipment	Acetone										
Thinner	If contents of can harden, add a couple drops of Acetone or Lacquer Brush Thinners.										
Flash Point	Approx 4°C. Inflammable.										
Drying Time	Up to two hours at 20°C according to thickness of layer. It is possible to apply several layers of Cetol Gupa within the space of one hour.										
Packaging	150mL & 750mL tins.										
Colour Range	<p>5 wood tones: Natural, Light Oak, Mahogany, Meranti (Cedar) and Teak. The following is a guide only to selecting the correct shade of Cetol Gupa when applying to bare wood. As timber colour varies, it is advisable to check / match colour on a test area or offcut.</p> <table> <tr> <td>Natural</td> <td>Radiata Pine - Douglas Fir - Spruce</td> </tr> <tr> <td>Light Oak</td> <td>Tasmanian Oak (Victorian Ash) — Cypress Pine — Tallowood — Pacific Maple (Meranti) — W.R. Cedar</td> </tr> <tr> <td>Mahogany</td> <td>Jarrah — Merbau (Kwila)</td> </tr> <tr> <td>Meranti (Cedar)</td> <td>W.R. Cedar — Pacific Maple</td> </tr> <tr> <td>Teak</td> <td>Teak - Rimu</td> </tr> </table>	Natural	Radiata Pine - Douglas Fir - Spruce	Light Oak	Tasmanian Oak (Victorian Ash) — Cypress Pine — Tallowood — Pacific Maple (Meranti) — W.R. Cedar	Mahogany	Jarrah — Merbau (Kwila)	Meranti (Cedar)	W.R. Cedar — Pacific Maple	Teak	Teak - Rimu
Natural	Radiata Pine - Douglas Fir - Spruce										
Light Oak	Tasmanian Oak (Victorian Ash) — Cypress Pine — Tallowood — Pacific Maple (Meranti) — W.R. Cedar										
Mahogany	Jarrah — Merbau (Kwila)										
Meranti (Cedar)	W.R. Cedar — Pacific Maple										
Teak	Teak - Rimu										